



DuPont™ AmberChrom™ CG161S Chromatography Resin

Reverse Phase Polymeric Resin for Purification of Peptides and Small Active Molecules

Key Features

- Rigid, insoluble, and mechanically stable structure.
- High surface area and unique pore size.
- Chemically stable to standard organic solvents and cleaning agents.
- Excellent technical and economical alternative to RPC silica.

Key Applications

- Adsorption and reverse phase liquid chromatography.
- Purification of peptides.
- Separation of nucleosides.
- Kinetic exclusion process.

Typical Properties

Physical Properties	
Copolymer	Crosslinked divinylbenzene
Matrix	Macroporous
Type	Adsorbent
Physical Form	Opaque, white, spherical beads
Nitrogen BET	
Surface Area	900 m ² /g
Porosity	0.65 mL/mL
Average Pore Diameter	150 Å

Chemical Properties	
Functional Group	None
Chemical Resistance	Insoluble in dilute solutions of acids or bases and common solvents: IPA, ACN, MeOH
Particle Size	
Particle Diameter, mean	35 µm
% 20 – 50 µm	≥ 80%

Suggested Operating Conditions

Maximum Recommended Operating Temperature	60°C (140°F)
pH range	1-14
Maximum Recommended Operating Pressure	5 bar (72.5 psi)

General Information

- DuPont™ AmberChrom™ CG161S resin is supplied in a 50% (by volume) slurry form in an aqueous 20% ethanol solution.
- AmberChrom™ CG161S resin can be cleaned in the column or removed from the column and treated in bulk.
- AmberChrom™ CG161S should be stored in the column or as bulk resin in 20% propanol, methanol, ethanol, or acetonitrile, preferably between 4°C and 25°C.
- The product can also be provided as a dry material upon request.

Important Information

- Polymeric adsorbents, as produced, contain by-products resulting from the manufacturing process. The user must determine the extent to which organic by-product must be removed for any particular use and establish techniques to assure that the appropriate level of purity is achieved for that use.
- Like any chromatographic stationary phase, a conditioning step with the working solvent must be performed before operation.
- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Regulatory Note

DuPont can provide regulatory support for AmberChrom™ CG161S Chromatography Resin to end users under confidentiality, upon request.



All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

Have a question? Contact us at:
www.dupont.com/water/contact-us

©2022 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

Form No. 45-D04060-en, Rev. 0
June 2022