



DuPont™ AmberChrom™ CG71C Chromatography Resin

Reverse Polymeric Resin for Purification Peptides and Small Active Ingredients

Key Features

- Rigid, insoluble, aliphatic (acrylic ester) polymer.
- Mechanically stable.
- Chemically robust to standard reversed-phase solvents and cleaning agents.
- Stable within the entire pH range. Alternative to RPC silica.
- Suitable for high-resolution, low-pressure chromatography.

Key Applications

- Separation of small peptides (growth hormones).
- Separation of small proteins.
- Separation of radioelements.

Typical Properties

Physical Properties	
Copolymer	Acrylic ester
Matrix	Macroporous
Type	Adsorbent
Physical Form	Opaque, white, spherical beads

Nitrogen BET	
Surface Area	560 m ² /g
Porosity	0.55 mL/mL
Average Pore Diameter	250 Å

Chemical Properties	
Functional Group	None
Chemical Resistance	Insoluble in dilute solutions of acids or bases and common solvents: IPA, ACN, MeOH

Particle Size	
Particle Diameter, mean	120 μm
% 80-160μm	≥ 80%

Suggested Operating Conditions

Maximum Recommended Operating Temperature	60°C (140°F)
pH Range	1-14
Maximum Recommended Operating Pressure	5 bar (72.5 psi)

General Information

- DuPont™ AmberChrom™ CG71C resin is supplied in a 50% (by volume) slurry form in an aqueous 20% ethanol solution.
- AmberChrom™ CG71C resin can be cleaned in the column or removed from the column and treated in bulk.
- AmberChrom™ CG71C should be stored in the column or as bulk resin in 20% propanol, methanol, ethanol or acetonitrile, preferably between 4°C and 25°C.
- The product can also be provided as a dry material upon request.

Important Information

- Polymeric adsorbents, as produced, contain by-products resulting from the manufacturing process. The user must determine the extent to which organic by-product must be removed for any particular use and establish techniques to assure that the appropriate level of purity is achieved for that use.
- Like any chromatographic stationary phase, a conditioning step with the working solvent must be performed before operation.
- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Regulatory Note

DuPont can provide regulatory support for AmberChrom™ CG71C Chromatography Resin to end users under confidentiality, upon request.



All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.