



DuPont™ AmberTec™ MR-450 UPW H/OH Ion Exchange Resin

Non-Separable, Uniform Particle Size, Mixed Bed Ion Exchange Resin for Final Polishing for the Semiconductor Industry

Description

DuPont™ AmberTec™ MR-450 UPW H/OH Ion Exchange Resin is an ultrapure water-grade, non-separable, homogeneous, mixed bed resin recommended as a point-of-use or non-regenerable mixed bed in the polishing loop to achieve sub-ppb levels of soluble silica, boron, sodium, potassium, sulfate, chloride, zinc, iron, and aluminum. This non-regenerable mixed bed resin is used for 2 – 3 years before replacement.

This homogeneous mixed bed contains 360- μm cation resin and 590- μm anion resin (mean particle size), thus providing efficient kinetics to achieve a higher operating capacity. The ratio of anion to cation in AmberTec™ MR-450 UPW H/OH is volumetrically optimized to achieve maximum removal of boron and silica.

Semiconductor-grade is characterized by the high conversion to ionic sites ($\geq 95.0\%$). As shown in Figure 2, the excellent rinse characteristics also allow very efficient online operation.



Applications

- Non-regenerable, polishing mixed bed

Historical Reference

AmberTec™ MR-450 UPW H/OH Ion Exchange Resin has previously been sold as DOWEX MONOSPHERE™ MR-450 UPW Ion Exchange Resin.

Typical Properties

Physical Properties		
	Cation Resin	Anion Resin
Copolymer	Styrene-divinylbenzene	Styrene-divinylbenzene
Matrix	Gel	Gel
Type	Strong acid cation	Strong base anion, Type I
Functional Group	Sulfonic acid	Trimethylammonium
Physical Form	Light amber, translucent, spherical beads	White to yellow, translucent, spherical beads


Chemical Properties		
Ionic Ratio	1:1	1:1
Ionic Form as Shipped	H ⁺	OH ⁻
Total Exchange Capacity	≥ 2.0 eq/L	≥ 1.1 eq/L
Water Retention Capacity	46 – 53%	55 – 65%
Ionic Conversion		
H ⁺	≥ 99%	
OH ⁻		≥ 95%
CO ₃ ²⁻		≤ 5.0%
Cl ⁻		≤ 0.1%

Particle Size ⁵		
Particle Diameter	360 ± 50 µm	590 ± 50 µm
Uniformity Coefficient	≤ 1.1	≤ 1.1
< 300 µm	≤ 0.2%	≤ 0.2%

Purity		
Metals, dry basis		
Na	≤ 20 mg/kg	≤ 25 mg/kg
Fe	≤ 25 mg/kg	≤ 25 mg/kg
Cu	≤ 10 mg/kg	≤ 15 mg/kg
Al	≤ 15 mg/kg	≤ 15 mg/kg

Hydraulic Characteristics

Estimated pressure drop for DuPont™ AmberTec™ MR-450 UPW H/OH Ion Exchange Resin as a function of service flowrate and temperature is shown in Figure 1. These pressure drop expectations are valid at the start of the service run with clean water.



Stability		
Whole Uncracked Beads	≥ 95%	≥ 95%
Friability		
Average	≥ 350 g/bead	≥ 350 g/bead
> 200 g/bead	≥ 95%	≥ 95%

Density	
Shipping Weight	704 g/L (AmberTec™ MR-450 UPW H/OH)

⁵ For additional particle size information, please refer to the [Particle Size Distribution Cross Reference Chart](#) (Form No. 45-D00954-en).

Suggested Operating Conditions

Temperature Range (H ⁺ /OH ⁻ form) [‡]	15 – 25°C (59 – 77°F)
pH Range (Stable)	0 – 14


[‡] Operating at elevated temperatures, for example above 60 – 70°C (140 – 158°F), may impact the purity of the loop and resin life. Contact our technical representative for details.

For additional information regarding recommended minimum bed depth, operating conditions, and regeneration conditions for [mixed beds](#) (Form No. 45-D01127-en) or [separate beds](#) (Form No. 45-D01131-en) in water treatment, please refer to our Tech Facts.

UPW Rinse Properties

AmberTec™ UP Ion Exchange Resins are especially processed and controlled in Quality to ensure the purest treated water quality for semiconductors applications. Typical rinse curves for conductivity and total organic carbon (TOC) as a function of rinse volume (in bed volumes) is shown in Figure 2.

Figure 2: Resistivity and TOC Rinse Performance



Product Stewardship

DuPont has a fundamental concern for all who make, distribute, and use its products, and for the environment in which we live. This concern is the basis for our product stewardship philosophy by which we assess the safety, health, and environmental information on our products and then take appropriate steps to protect employee and public health and our environment. The success of our product stewardship program rests with each and every individual involved with DuPont products—from the initial concept and research, to manufacture, use, sale, disposal, and recycle of each product.

Customer Notice

DuPont strongly encourages its customers to review both their manufacturing processes and their applications of DuPont products from the standpoint of human health and environmental quality to ensure that DuPont products are not used in ways for which they are not intended or tested. DuPont personnel are available to answer your questions and to provide reasonable technical support. DuPont product literature, including safety data sheets, should be consulted prior to use of DuPont products. Current safety data sheets are available from DuPont.

Please be aware of the following:

WARNING: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.



Have a question? Contact us at:
[dupont.com/water/contact-us](https://www.dupont.com/water/contact-us)

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DUPONT ASSUMES NO OBLIGATION OR LIABILITY FOR THE INFORMATION IN THIS DOCUMENT. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours Inc. unless otherwise noted. © 2024 DuPont. All rights reserved.

Form No. 45-D00880-en, Rev.2
May 2024