

Microbial Barrier Properties of 1073B and 1059B Transition Protocol Materials



Property	Comparable Test Method	Units	Current Typical Value Tyvek® 1073B	Transition Protocol Target Value Tyvek® 1073B	1073B Transition Protocol Typical Value	Current Typical Value Tyvek® 1059B	Transition Protocol Target Value Tyvek® 1059B	1059B Transition Protocol Typical Value
Microbial Barrier	ASTM F1608	LRV	>5	>5	>5	>4	>4	>4
Microbial Barrier	ASTM F2638	% pMax	<0.3	<0.3	<0.3	<0.5	<0.5	<0.5

Notes: 1073B and 1059B Transition Protocol typical values represent data across different line and polymer combinations from a limited number of manufacturing campaigns. Values will be refreshed, as necessary, upon data collection from additional campaigns and long-term variability discernment.