

DuPont™ Kalrez® 8475

For Semiconductor Oxidation and Diffusion Applications

Technical Information - March, 2017

Product Description

DuPont™ Kalrez® 8475 perfluoroelastomer parts are a white product that have been specifically developed to meet the challenging requirements associated with oxidation and diffusion applications. It exhibits excellent thermal stability and long-term sealing performance and significantly reduced outgassing properties at elevated temperatures. Kalrez® 8475 has good mechanical properties and is well-suited for static and low stress/low sealing force applications (e.g., quartz tube seals, ball joint seals, bell jar seals, plenum seals). A maximum application temperature of 300°C (572°F) is suggested. Ultrapure post-cleaning and packaging is standard for all 8475 parts.

Product Features Contribute to Extended Seal Life

- Very low outgassing
- Excellent resistance to “dry” gas process environments
- Improved (lower) compression set
- Excellent long-term seal force retention

Suggested Applications

- Quartz tube seals
- Ball joint seals
- Gas feedthrough seals
- Bell jar seals
- Plenum seals
- Other thermal applications

Typical Physical Properties¹

Color	White
Hardness, Shore A (pellet) ²	62
Hardness, Shore M (O-ring) ³	74
100% Modulus ⁴ , MPa (psi)	2.49 (361)
Tensile Strength at Break ⁴ , MPa (psi)	14.61 (2119)
Elongation at Break ⁴ , %	222
Comp. Set ⁵ , %, 70 hr. at 204 °C (400°F)	20
Max. Application Temperature ⁶ , °C (°F)	300 (572)

¹ Not to be used for specification purposes

² ASTM D2240 (pellet test specimens)

³ ASTM D2240 and ASTM D1414 (AS568 K214 O-ring test specimen)

⁴ ASTM D412 (dumbbell test specimens)

⁵ ASTM D395B and ASTM D1414 (AS568 K214 O-ring test specimens)

⁶ DuPont proprietary test method

Typical O-Ring Compression Set Properties¹

Material Tested	% C/S at		
	204°C	250°C	300°C
Kalrez® 8475	20	30	45
Kalrez® 4079	37	41	45
Competitive FFKM A2	43	100	Sample Failed

¹ASTM D 395B and D1414 (AS568 K214 O-ring test specimens)



The miracles of science™

**Kalrez® 8475—Minimal Outgassing at Elevated Service Temperatures
TG-MS Outgassing Analysis* (Room Temperature to 400°C at 10°C/min)**

Gas Evolved	R.T. to 100°C,	R.T. to 200°C,	R.T. to 300°C,	R.T. to 400°C,
	ppm	ppm	ppm	ppm
H ₂ O	2	255	324	345
HF+	0	0	0	1
CF+	0	0	0	12
CO ₂	0	0	2	103
CF ₂	0	0	0	19
CHF+	0	0	0	20
CF ₃ +	0	0	0	119
C ₂ F ₃ +	0	0	0	23
CF ₃ O+	0	0	0	0
C ₂ F ₄ +	0	0	0	9
C ₂ F ₅ +	0	0	0	1
C ₃ F ₅ +	0	0	0	31
Total Outgas, %	0.00	0.03	0.03	0.07
Weight Loss, %	0.00	0.00	0.01	0.07

* Data provided by independent testing laboratory.

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America
800-222-8377

Latin America
+0800 17 17 15

Europe, Middle East, Africa
+41 22 717 51 11

Greater China
+86-400-8851-888

ASEAN
+65-6586-3688

Japan
+81-2-5521-8484

The information provided in this data sheet corresponds to DuPont knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise.

The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use and disposal conditions, DuPont does not guarantee results, makes no warranties and assumes no liability in connection with any use of this information. All such information is given and accepted at the buyer's risk. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent.

CAUTION: Do not use DuPont materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-5 and DuPont CAUTION Regarding Medical Applications H-50102-5.

Copyright © DuPont. The DuPont Oval Logo, DuPont™, The miracles of science™, Kalrez® is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(03/17) Reference No. KZE-H82172-00-J0317



The miracles of science™