

# PRODUCT DATA

## AURUM<sup>®</sup> PL450C Thermoplastic Polyimide

TYPICAL PROPERTIES	TEST METHOD	UNITS	VALUE
<b>PHYSICAL</b>			
Specific Gravity	ASTM D-792	–	1.33
Mold Shrinkage	ASTM D-955	%	0.83
Water Absorption 24 hrs @ 73°F	ASTM D-570	%	0.34
Moisture Absorption, 24 Hrs.	73°F, 60%RH	%	0.24
<b>MECHANICAL</b>			
Tensile Strength	73°F 300°F	ASTM D-638 "	psi (MPa) " 13,370 (92) 8,400 (58)
Elongation	73°F 300°F	ASTM D-638 "	% " 90 90
Flexural Strength	73°F 300°F	ASTM D-790 "	psi (MPa) " 19,900 (137) 12,800 (88)
Flexural Modulus	73°F 300°F	ASTM D-790 "	psi (MPa) " 426,800 (2,940) 369,900 (2,550)
Izod Impact Strength (notched)		ASTM D-256	ft lb/in (J/m) 1.7 (90)
Compressive Strength	73°F 300°F	JIS K-7208 "	psi (MPa) " 17,360 (120) 11,100 (76)
Youngs Modulus		ASTM D-882	psi (MPa) 400,000 (2,760)
<b>THERMAL</b>			
Melt Point		DSC	°F (°C) 730 (388)
Glass Transition Temperature		DSC	°F (°C) 482 (250)
Melt Flow Index 752°F, 2.3 lbs.		ASTM D-1238	g/10 min 4.5~7.5
Coefficient of Thermal Expansion (MD/TD) 73°F		ASTM D-696	10 <sup>-5</sup> /°F (10 <sup>-5</sup> /°C) 3.0/3.0 (5.5/5.5)
Heat Deflection Temperature		ASTM D-648	°F (°C) 460 (238)
Thermal Conductivity		ASTM C-177	Kcal/m hr °C 0.15
Specific Heat	73°F 212°F 572°F	DSC " "	Cal/g °C 0.24 " 0.24 " 0.34
<b>ELECTRICAL</b>			
Dielectric Constant	1KHz 1MHz	ASTM D-150 "	– – 3.2 3.1
Dissipation Factor	1KHz 1MHz	ASTM D-150 "	– – 0.0009 0.0034
Surface Resistivity		ASTM D-257	Ohms E17~E18
Volume Resistivity		"	Ohm cm E17~E18
<b>FLAMMABILITY</b>			
Vertical Burn Test	0.4 mm 2.0 mm	UL-94 "	– – V-0 5VA
Oxygen Index	3.2 mm	ASTM D-2863	% 47

### DESCRIPTION

AURUM PL450C is a high performance thermoplastic polyimide for precision injection molded components and extruded products. A member of the AURUM family of advanced engineering resins, unfilled AURUM PL450C offers a unique balance of mechanical and thermal properties for superior performance in demanding automotive, business machinery, industrial equipment, aerospace, and semiconductor equipment applications. AURUM exhibits outstanding resistance to chemicals and radiation, a low coefficient of thermal expansion, ultra-high purity, low outgassing in a vacuum, excellent electrical properties, and flame resistance. AURUM PL450C can be conventionally extruded to produce high performance wire & cable insulation, thin-wall tubing, and fiber.

### INJECTION MOLDING

AURUM PL450C can be readily injection molded in most reciprocating screw injection molding machines. AURUM resin pellets should be dried prior to melt processing on trays in an air circulation oven or desiccating hopper drier under the following conditions: 8 hours at 428°F, 10 hours at 392°F, or 12 hours at 356°F. Cylinder temperature requirements generally range from 720 - 770°F. Injection pressures of 11,000 - 20,000 psi, nominal back pressures of 0 - 50 psi, medium to high injection velocity, and screw speeds of 100 - 200 rpm are utilized for AURUM injection molding. Mold temperatures range from 356 - 410°F. AURUM sprue and runner systems can be ground and mixed with virgin AURUM resin at 15% - 30% levels without significant loss of mechanical properties for enhanced economics. AURUM can be easily

(continued from front)

purged with unfilled or glass fiber reinforced polyethersulfone, polysulfone, or polyetherimide. AURUM can be injection molded with select outer-heating design hot runner systems.

## **APPLICATIONS**

AURUM PL450C injection molded components are excellent replacements for metals, ceramics, and other plastics. High performance AURUM PL450C parts include heat-resistant gears, seals, ferrules and other fasteners, coil

bobbins, semiconductor manufacturing and handling equipment components, and thermal and electrical insulators. Products produced from extruded AURUM PL450C resin include thin-wall tubing, wire and cable insulation, monofilament, and rod stock shapes.

**CAUTION! DO NOT USE AURUM®(A) IN MEDICAL APPLICATIONS INVOLVING IMPLANTATION IN THE HUMAN BODY OR (B) IN CONTACT WITH INTERNAL BODY FLUIDS OR TISSUES. AURUM® WAS NOT DESIGNED OR MANUFACTURED FOR SUCH PURPOSES.**

**NO REPRESENTATION, PROMISE, EXPRESS WARRANTY OR IMPLIED WARRANTY IS MADE CONCERNING THE SUITABILITY OF AURUM® FOR USE IN IMPLANTATION IN THE HUMAN BODY OR IN CONTACT WITH INTERNAL BODY FLUIDS OR TISSUES.**

**AURUM® IS NOT RECOMMENDED, AUTHORIZED OR APPROVED FOR IMPLANTS. CLINICAL TESTING HAS NOT BEEN CONDUCTED TO DETERMINE THE SUITABILITY OF AURUM® FOR IMPLANTATION.** Because all implantable medical devices carry risk of failure and resulting adverse consequences, such testing should be conducted before and such implantation occurs to determine the effectiveness and safety of such use. Approval has neither been sought, nor received, from the FDA or any other governmental authority for use of AURUM® in implantation in the human body or in contact with internal body fluids or tissues.

**DO NOT MAKE REFERENCE TO THE AURUM® NAME OR TRADEMARK OR TO THE NAME OF MANUFACTURER OR OTHER SUPPLIER OF AURUM® IN ASSOCIATION WITH AN APPLICATION MEDICAL DEVICE.**

**IMPORTANT:** Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, MTC makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or industrial hygiene requirements associated with particular uses of any product described herein. Nothing contained in this bulletin shall be considered a recommendation for any use that may infringe patent rights or an endorsement of any particular material not supplied by MTC. The "Properties" and "Applications" listed in this bulletin are not specifications. They are provided as information only and in no way modify, amend or enlarge and specification or warranty.