DuPont™ AmberChrom™ 1X4 100-200 Cl Chromatography Resin

Ion Exchange Resin for Purification of Small Active Molecules

Key Features

- Strong type I anion exchange with a 4% crosslinking level.
- Controlled particle size with a low level of fines.
- Strong insoluble structure resulting in a high resistance to oxidation, reduction, mechanical wear and breakage.

Key Applications

- Separation and isolation of amino acids.
- Desalting and concentration after fermentation.

Typical Properties

Physical Properties	
Copolymer	Styrene-divinylbenzene
Matrix	Gel
Type	Anion exchange resins
Functional Group	Trimethylammonium
Physical Form	Opaque, white, spherical beads
Chemical Properties	
Ionic Form as Shipped	Cl^-
Water Retention Capacity	53-63%
Total Exchange Capacity	≥ 1.0 Eq/L

Particle Size	
< 8 µm	≤ 10%
> 250 µm	≤ 15%
Stability	
Whole Uncracked Beads	≥ 90%
Swelling	$Cl^- \rightarrow OH^-$ ≤ 20%
Density	
Shipping Weight	705 g/L

Suggested Operating Conditions

Temperature Range	
OH^-	5 – 60°C (41 – 140°F)
Cl^-	5 – 100°C (41 – 212°F)
pH Range	1 – 14

General Information

- The operational stability of ion exchange resins is largely defined by the particular process involved. Therefore, stability testing under actual process conditions is an important part of the resin evaluation and selection process. Ion exchange resins are tolerant of a wide range of chemical conditions and can be washed over the entire pH range without ill effects.
- Slower degradation with oxygen may be catalytically induced. Therefore, exposure of resins to metal ions (including iron, manganese and copper) should be minimized in oxidizing environments. The physical stability of resins is also affected by the method of product handling. Deep resin beds, small diameter beds, very high flow rates and frequent pumping or agitation all can contribute to resin attrition breakage.

Important Information

- **WARNING:** Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DuPont assumes no obligation or liability for the information in this document. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

Have a question? Contact us at:
www.dupont.com/water/contact-us

© 2022 DuPont. DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, ℠ or ® are owned by affiliates of DuPont de Nemours Inc., unless otherwise noted.

Form No . 45-D04077-en, Rev. 0
June 2022