



Ion Exchange

Pressurized Water Reactor

Condensate Polisher

Condensate polishers protect critical steam generator components from potential condenser leaks, thereby improving plant reliability. Our ion exchange resins have been the backbone of condensate polishing systems throughout the world for decades. Depending on the chemistry used in the steam generator feed water, the right resin combination will help provide the optimum performance in terms of treated condensate purity and cycle run length.

PRODUCT	AMINE	CATION PRE-BED	FEATURES AND RECOMMENDED USES	TYPE	MATRIX	TOTAL VOLUME CAPACITY (eq/L, min)	IONIC FORM AS SHIPPED
DuPont™ AmberLite™ HPR550 OH	NH ₄ / Organic Amine	N/A	By far the most common resin combination used worldwide for pressurized water reactor condensate polishing applications. This pairing offers the best balance of properties: high-capacity gel type resins, uniform particle size, and high physical stability. AmberLite™ HPR650 H Resin is also an excellent choice for cation pre-beds required to handle NH ₄ / amine load.	SBA	GEL	1.10	OH-
DuPont™ AmberLite™ HPR650 H		Yes		SAC	GEL	2.00	H+
DuPont™ AmberLite™ HPR550 OH	NH ₄ / Organic Amine	N/A	Pairing that offers one of the highest NH ₄ / amine capacities with good anion protection, allowing enhanced pH for better FAC control. AmberLite™ HPR1600 H Resin provides high NH ₄ /amine capacity for cation pre-beds.	SBA	GEL	1.10	OH-
DuPont™ AmberLite™ HPR1600 H		Yes		SAC	GEL	2.40	H+
DuPont™ AmberLite™ HPR9000 OH	NH ₄ / Organic Amine	N/A	Pairing that offers high NH ₄ /amine capacity with good anion protection. AmberLite™ HPR1600 H Resin provides high NH ₄ /amine capacity for cation pre-beds. The use of a macroporous anion resin provides excellent resistance to surface fouling and kinetic impairment.	SBA	MACRO	0.80	OH-
DuPont™ AmberLite™ HPR1600 H		Yes		SAC	GEL	2.40	H+
DuPont™ AmberLite™ HPR9000 OH	ETA	N/A	The only ion exchange resin pair shown to mitigate ETA chemistry related anion resin kinetic impairment. Designed specifically for use with ETA chemistry.	SBA	MACRO	0.80	OH-
DuPont™ AmberLite™ HPR1400 H		No		SAC	GEL	2.00	H+
DuPont™ AmberLite™ HPR9000 OH	Organic Amines	N/A	Pairing that offers high Na selectivity for operation past amine break. The use of a macroporous anion resin provides excellent resistance to surface fouling and kinetic impairment.	SBA	MACRO	0.80	OH-
DuPont™ AmberLite™ HPR2000 H		No		SAC	MACRO	1.70	H+
DuPont™ AmberLite™ IRN360 H/OH	Non Regenerable Start-up	N/A	Ready to use gel type mixed bed composed of 2/3 of high-capacity UPS cation resin AmberLite™ IRN97 H and 1/3 IRN78 OH Resins on a volume basis. High cation dosage volume allows high maximum exchange capacity when cation species are dominant (alkaline pH), in all PWR applications.	MB	GEL/GEL	2.10/1.20	H+/OH-
DuPont™ AmberLite™ 600i	Layer Separation	N/A	Inert interface separator compatible with all PWR condensate polishing resin pairs.	Inert	GEL	N/A	N/A

Key:

CPP = Condensate Polishing Plant
RWCU = Reactor Water Clean Up
SBA = Strong Base Anion
SAC = Strong Acid Cation
MB = Mixed Bed

Powering performance worldwide.

With a large global manufacturing footprint, strong R&D expertise and technical support services and systems, we supply high market volumes with high quality. DuPont partners with you, our customer, to understand unmet needs and develop tailored solutions.

TECHNICAL SERVICE, RESEARCH & DEVELOPMENT

Chauny, France*
Edina, MN, USA
Huzhou, China
Hyderabad, India
KAUST Jeddah, KSA
Midland, MI, USA
Shanghai, China Singapore
Tarragona, Spain*
Wilmington, DE, USA

COMMERCIAL OPERATIONS

Astana, Kazakhstan
Bangkok, Thailand
Beijing, China
Bogota, Colombia
Buenos Aires, Argentina
Budapest, Hungary
Dubai, UAE
Chengdu, China
Delhi, India
Edina, MN, USA
Guangzhou, China
HCM City, Vietnam
Hong Kong, China
Jakarta, Indonesia
Johannesburg, South Africa
Kuala Lumpur, Malaysia
Madrid, Spain

Manila, Philippine
Melbourne, Australia
Mexico City, Mexico
Midland, MI, USA
Moscow, Russia
Mumbai, India Nairobi,
Kenya
Paris, France São
Paulo, Brazil
Seoul, Republic of Korea
Pfaeffikon, Switzerland
Shanghai, China Singapore
Surubya, Indonesia Taipei,
Taiwan Tokyo, Japan
Warsaw, Poland

MANUFACTURING

Chauny, France
Edina, MN, USA
Fombio, Italy
Huzhou, China
Jubail Industry
City, Saudi
Arabia Midland,
MI, USA
Qingpu, China
Soma, Japan



Have a question? Contact us at:

www.dupont.com/water/contact-us

All information set forth herein is for informational purposes only. This information is general information and may differ from that based on actual conditions. Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other government enactments. The product shown in this literature may not be available for sale and/or available in all geographies where DuPont is represented. The claims made may not have been approved for use in all countries. Please note that physical properties may vary depending on certain conditions and while operating conditions stated in this document are intended to lengthen product lifespan and/or improve product performance, it will ultimately depend on actual circumstances and is in no event a guarantee of achieving any specific results. DUPONT ASSUMES NO OBLIGATION OR LIABILITY FOR THE INFORMATION IN THIS DOCUMENT. References to "DuPont" or the "Company" mean the DuPont legal entity selling the products to Customer unless otherwise expressly noted. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED. No freedom from infringement of any patent or trademark owned by DuPont or others is to be inferred.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted. © 2023 DuPont. All right reserved