



NG273B WH

DuPont™ ProShield® 60

DuPont™ ProShield® 60 Bib Apron. 28" x 36". Neck Loop & Waist Ties. Bound Seams. White.

Name	Description
Full Part Number	NG273BWHxx0100yy (xx=size;yy=option code)
Fabric/Materials	PROSHIELD® 60
Design	Bib Apron
Seam	Bound
Color	White
Quantity/Box	100 per case
Sizes	00
Option Codes	00

FEATURES & PRODUCT DETAILS

ProShield® 60 garments are suitable for protection against non-hazardous particles, light liquid splash and aerosols in many

• Provides protection from light liquid splash and aerosols in many industrial applications. ProShield® 60 garments are made with a microporous film that is laminated to a spundbonded polypropylene substrate. Applications include: automotive refinishing, waste cleanup, asbestos abatement, and hazardous remediation.


- Bound seams around neck
- Ties at waist
- Manufactured under specifications that do not contain natural rubber latex.
- One size fits most

AVAILABLE OPTIONS

Option Code	Description	Sizes	Part Number
00	Standard	UNI	NG273BWHxx010000

SPECIFICATIONS

- The garment shall be constructed of DuPont™ ProShield® 60 -- a composite of microporous film and nonwoven fabric.
- The garment shall be white in color.
- The garment shall be a bib apron design.
- The garment shall have bound seams.
- The garment shall have a neck loop.
- The garment shall have waist ties.
- The garment shall be 36" in length.



FINISHED DIMENSIONS

Size	Body Length	Body Width
UNI	35 3/4	27

ADDITIONAL EQUIPMENT NEEDED

- This garment only provides partial body coverage. It may be worn in combination with other chemical resistant PPE as required based on the hazard assessment.
- Wear other appropriate PPE such as, but not limited to, respiratory, eye, head, hand, and foot protection based on the hazard assessment.

Physical Properties



Data relating to mechanical performance of the fabrics used in DuPont chemical protective clothing, listed for the selected garment according to the test methods and relevant European standard, if applicable. Such properties, including abrasion and flex-cracking resistance, tensile strength and puncture resistance can help in the assessment of protective performance.

Property	Test Method	Typical Result
Thickness (PPSH-249)	ASTM D751	10 mils
Basis Weight	ASTM D751	1.8 oz/yd ²
Tear Resistance - Trap Tear (MD)	ASTM D1117	11 lb _f
Tear Resistance - Trap Tear (CD)	ASTM D1117	7 lb _f
Breaking Strength - Grab (MD).	ASTM D5034	23 lb _f
Breaking Strength - Grab (CD)	ASTM D5034	11 lb _f
Hydrostatic Head	AATCC 127	68 inches H ₂ O
Surface Resistivity (25°C / 55% RH)	ASTM D257 (1081)	1.0 x 10 ⁹ ohms/square
Wearing Apparel Flammability	16 CFR 1610	Class 1

SPECIAL WARNINGS

- *Serged and bound seams are degraded by some hazardous liquid chemicals, such as strong acids, and should not be worn when these chemicals are present.
- *Liquid barrier performance varies based on the amount of liquid that may get on the garment, the length of time the liquid is on the garment, applied pressure and certain physical properties of the liquid. Tyvek®400, Tyvek® 400 D, ProShield®, ProShield® 10, ProShield® 60, Tyvek® 400 FC, and ProShield® 70 garments are not appropriate if during use they are getting wet (liquid is dripping or running, or it is wet to the touch) or if spotting is observed on skin or garments worn under the protective garment. Tyvek® 500 and Tyvek® 600 offer improved liquid barrier, but may not be appropriate if spotting is observed on the skin or garments worn under the protective garment. In applications where a higher liquid barrier is needed, consider Tychem® 2000 and Tychem® 4000 garments with taped seams.
- *CAUTION: This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is the user's responsibility to determine the level of toxicity and the proper personal protective equipment needed. The information set forth herein reflects laboratory performance of fabrics, not complete garments, under controlled conditions. It is intended for informational use by persons having technical skill for evaluation under their specific end-use conditions, at their own discretion and risk. Anyone intending to use this information should first verify that the garment selected is suitable for the intended use. In many cases, seams and closures have shorter breakthrough times and higher permeation rates than the fabric. Please contact DuPont for specific data. If fabric becomes torn, abraded or punctured, or if seams or closures fail, or if attached gloves, visors, etc. are damaged, end user should discontinue use of garment to avoid potential exposure to chemical. Since conditions of use are outside our control, we make no warranties, express or implied, including, without limitation, no warranties of merchantability or fitness for a particular use and assume no liability in connection with any use of this information. This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

Cellosolve® and Selexol™ are registered trademarks of Dow Chemicals Company. Skydrol® is a registered trademark of Solutia.

- Tyvek® 500, Tyvek® 600, Tyvek® 800 products manufactured before January 2023 did contain natural rubber latex which may cause allergic reactions in some sensitized individuals. Anyone who begins to exhibit an allergic response during the use of DuPont products should immediately cease using these products. The incident should also be reported to DuPont at +1 (888) 439-2988 so that an investigation can be initiated.