



FC450S GY

DuPont™ Tyvek® 400 FC

DuPont™ Tyvek® 400 FC Shoe Cover with Tyvek® 400 FC Skid-Resistant Sole. 5" High. Serged Seams. Gray.

Name	Description
Full Part Number	FC450SGYxx0200yy (xx=size;yy=option code)
Fabric / Material	Tyvek® 400 FC
Design	Shoe Cover
Seam	Serged
Color	Gray
Quantity/Box	200 per case
Sizes	00
Option Codes	NF

FEATURES & PRODUCT DETAILS

Tyvek® 400 FC -- a DuPont™ Tyvek® protective fabric with a skid resistant friction coating. Used exclusively for shoe and boot covers and skid-resistant boots.


- Slip-resistant boots
- Sole material composed of Tyvek® 400 FC, a special coating to provide added slip-resistance.
- One size fits most

AVAILABLE OPTIONS

Option Code	Description	Sizes	Part Number
00	Standard (00)	00	FC450SGYxx020000
NF	NAFTA sourced	00	FC450SGYxx0200NF

SPECIFICATIONS

- The garment shall be constructed of DuPont™ Tyvek® 400 FC -- a DuPont™ Tyvek® protective fabric with a skid resistant friction coating.
- The garment shall be gray in color.
- The garment shall be a shoe cover design.
- The garment shall have serged seams.
- The garment shall have an elastic opening, toe, sole and heel seam.
- The garment shall have a Tyvek® 400 FC upper.
- The garment shall have soles made of Tyvek® FC skid-resistant material..
- The garment shall be 5™ high.



FINISHED DIMENSIONS

Size	Sleeve Length	Chest Width	Inseam	Fits Chest	Fits Height	Boot Length	Boot Height	Mens Shoe	Womens Shoe	Inner Glove Size	C
00	n/a	n/a	n/a	n/a	n/a - n/a	17 1/2	5	n/a	n/a	n/a	n

ADDITIONAL EQUIPMENT NEEDED

- This garment only provides partial body coverage. It may be worn in combination with other chemical resistant PPE as required based on the hazard assessment.
- Wear other appropriate PPE such as, but not limited to, respiratory, eye, head, hand, and foot protection based on the hazard assessment.

Physical Properties



Data relating to mechanical performance of the fabrics used in DuPont chemical protective clothing, listed for the selected garment according to the test methods and relevant European standard, if applicable. Such properties, including abrasion and flex-cracking resistance, tensile strength and puncture resistance can help in the assessment of protective performance.

Property	Test Method	Typical Result
Thickness	ASTM D1117	7.4 mils
Basis Weight	ASTM D3776	1.6 oz/yd ²
Tear Resistance - Trap Tear (MD)	ASTM D5733	5 lb _f
Tear Resistance - Trap Tear (CD)	ASTM D5733	7 lb _f
Breaking Strength - Grab (MD)	ASTM D5034	20 lb _f
Breaking Strength - Grab (CD)	ASTM D5034	26 lb _f
Hydrostatic Head	AATCC 127	4.2 inches H ₂ O
Wearing Apparel Flammability	16 CFR 1610	Class 1

SPECIAL WARNINGS

- *Serged and bound seams are degraded by some hazardous liquid chemicals, such as strong acids, and should not be worn when these chemicals are present.
- *Liquid barrier performance varies based on the amount of liquid that may get on the garment, the length of time the liquid is on the garment, applied pressure and certain physical properties of the liquid. Tyvek®400, Tyvek® 400 D, ProShield®, ProShield® 10, ProShield® 60, Tyvek® 400 FC, and ProShield® 70 garments are not appropriate if during use they are getting wet (liquid is dripping or running, or it is wet to the touch) or if spotting is observed on skin or garments worn under the protective garment. Tyvek® 500 and Tyvek® 600 offer improved liquid barrier, but may not be appropriate if spotting is observed on the skin or garments worn under the protective garment. In applications where a higher liquid barrier is needed, consider Tychem® 2000 and Tychem® 4000 garments with taped seams.
- *Tyvek® 400 FC fabric was specially treated to promote ink / coating adhesion. This treatment lowers the bulk liquid holdout level below the typical level for standard Tyvek® fabric. If protection from liquid splash is required, please consider a non-treated Tyvek® style or Tychem® fabric substrate garment.
- *CAUTION: This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is the user's responsibility to determine the level of toxicity and the proper personal protective equipment needed. The information set forth herein reflects laboratory performance of fabrics, not complete garments, under controlled conditions. It is intended for informational use by persons having technical skill for evaluation under their specific end-use conditions, at their own discretion and risk. Anyone intending to use this information should first verify that the garment selected is suitable for the intended use. In many cases, seams and closures have shorter breakthrough times and higher permeation rates than the fabric. Please contact DuPont for specific data. If fabric becomes torn, abraded or punctured, or if seams or closures fail, or if attached gloves, visors, etc. are damaged, end user should discontinue use of garment to avoid potential exposure to chemical. Since conditions of use are outside our control, we make no warranties, express or implied, including, without limitation, no warranties of merchantability or fitness for a particular use and assume no liability in connection with any use of this information. This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

Cellosolve® and Selexol™ are registered trademarks of Dow Chemicals Company. Skydrol® is a registered trademark of Solutia.