



IC461S option 0B

# DuPont™ Tyvek® IsoClean®

DuPont™ Tyvek® IsoClean® Shoe Cover. Serged Seams. PVC Sole. Elastic Opening. Elastic Toe. 5" High. White.

| Name             | Description                |
|------------------|----------------------------|
| Full Part Number | IC461SWHxx0300yy (xx=size) |
| Fabric/Materials | TYVEK® ISOCLEAN®           |
| Design           | Shoe Covers                |
| Seam             | Serged                     |
| Color            | White                      |
| Quantity/Box     | 300 per case               |
| Sizes            | SM, MD, LG, XL             |
| Option Codes     | 0B                         |

## FEATURES & PRODUCT DETAILS

Tyvek® IsoClean® delivers an ideal balance of protection, durability and comfort. Made using a patented flash spinning process, Tyvek® provides an impenetrable barrier to particles, microorganisms and non-hazardous liquid splash.


- Sealed seams have multiple interlocking threads that sewn around the entire edge of garment.
- 5" shoe cover with elastic top
- Elastic at the toe for a more secure fit
- PVC soles provides enhanced skid-resistance and durability
- Bulk packaged in double transparent poly liners.
- Manufactured under specifications that do not contain natural rubber latex.

AVAILABLE OPTIONS

| Option Code | Description | Sizes       | Part Number      |
|-------------|-------------|-------------|------------------|
| 0B          | Bulk        | SM,MD,LG,XL | IC461SWHXL03000B |

## SPECIFICATIONS

- The garment shall be white in color.
- The garment shall be a shoe cover design.
- The garment shall have serged seams.
- The garment shall have a Tyvek® 400 upper.
- The garment shall have soles made of PVC.
- The garment shall be 5™ high.



**FINISHED DIMENSIONS**

| Size | Boot Length | Boot Height |
|------|-------------|-------------|
| SM   | 9 1/2       | 5 1/4       |
| MD   | 11          | 5 1/4       |
| LG   | 14          | 5 1/4       |
| XL   | 15 1/2      | 5 1/4       |

#### **ADDITIONAL EQUIPMENT NEEDED**

- This garment only provides partial body coverage. It may be worn in combination with other chemical resistant PPE as required based on the hazard assessment.
- Wear other appropriate PPE such as, but not limited to, respiratory, eye, head, hand, and foot protection based on the hazard assessment.

## Physical Properties



Data relating to mechanical performance of the fabrics used in DuPont chemical protective clothing, listed for the selected garment according to the test methods and relevant European standard, if applicable. Such properties, including abrasion and flex-cracking resistance, tensile strength and puncture resistance can help in the assessment of protective performance.

| Property                                        | Test Method      | Typical Result                      | stdDev |
|-------------------------------------------------|------------------|-------------------------------------|--------|
| Basis Weight                                    | ASTM D3776       | 1.22 oz/yd <sup>2</sup>             |        |
| Bacterial Filtration Efficiency<br>(3.0 micron) | ASTM F2101       | 99.0                                |        |
| Burst Strength - Mullen.                        | ASTM D774        | 54 psi                              |        |
| Breaking Strength - Grab (MD).                  | ASTM D5034       | 18 lb <sub>f</sub> /in              |        |
| Breaking Strength - Grab (CD)                   | ASTM D5034       | 23 lb <sub>f</sub> /in              |        |
| Surface Resistivity (25°C / 55% RH)             | ASTM D257 (1081) | < 6.3 x 10 <sup>9</sup> ohms/square |        |
| Hydrostatic Head                                | AATCC 127        | 91 cm H <sub>2</sub> O              |        |
| Wearing Apparel Flammability                    | 16 CFR 1610      | Class 1                             |        |

## SPECIAL WARNINGS

- Seams and closures have less barrier than fabric.
- Note: for protection from hazardous or infectious liquids, additional barrier tests are required to establish suitability for use.
- \*CAUTION: This information is based upon technical data that DuPont believes to be reliable. It is subject to revision as additional knowledge and experience are gained. DuPont makes no guarantee of results and assumes no obligation or liability in connection with this information. It is the user's responsibility to determine the level of toxicity and the proper personal protective equipment needed. The information set forth herein reflects laboratory performance of fabrics, not complete garments, under controlled conditions. It is intended for informational use by persons having technical skill for evaluation under their specific end-use conditions, at their own discretion and risk. Anyone intending to use this information should first verify that the garment selected is suitable for the intended use. In many cases, seams and closures have shorter breakthrough times and higher permeation rates than the fabric. Please contact DuPont for specific data. If fabric becomes torn, abraded or punctured, or if seams or closures fail, or if attached gloves, visors, etc. are damaged, end user should discontinue use of garment to avoid potential exposure to chemical. Since conditions of use are outside our control, we make no warranties, express or implied, including, without limitation, no warranties of merchantability or fitness for a particular use and assume no liability in connection with any use of this information. This information is not intended as a license to operate under or a recommendation to infringe any patent or technical information of DuPont or others covering any material or its use.

Cellosolve® and Selexol™ are registered trademarks of Dow Chemicals Company. Skydrol® is a registered trademark of Solutia.

- Data presented does not comprise a product specification.